

ENZINRON (ESD ABS)

	METHOD	UNIT	VALUE
Mechanical Properties			
Specific gravity	ASTM D792	g/cm ³	1.07
Tensile yield strength	ASTM D638	Mpa	50
Breaking elongation	ASTM D638	%	40
Bending strength	ASTM 790	Mpa	60
Flexural modulus	ASTM 790	Mpa	1800
Shore hardness	ASTM D2240	D	80
Impact strength	ASTM D256	J/M	200
Thermal Properties			
Melting point	DSC	°C	150
Heat distortion temperature	ASTM D648	°C	90
Operating temperature	-	°C	80
Maximum operating temperature	-	°C	100
Thermal conductivity	DIN 52612- 1	W/(K-M)	0.17
Coefficient of linear thermal	ASTM D696	10 ⁻⁵ - 1/K	8
Electrical Properties			
Dielectric strength	ASTM D150	KV-mm	-
Dielectric loss factor	ASTM D150	-	-
Volume resistivity	ASTM D257	Ω.cm	10 ⁶⁻⁹
Surface resistivity	ASTM D257	Ω	10 ⁶⁻⁹
Dielectric constant	ASTM D149	-	-
Chemical Properties			
Water absorption	23°C 60%RH	%	0.4
Acid resistance	23°C 60%RH		+
Alkali resistance			0
Acid and alkali resistance			+
Resistance to sodium chlorate			0
Resistance to aromatic compounds			-
Resistance to ketone	23°C 60%RH		-
Resistance to hot water	23°C 60%RH		0
Others			
Flammability	UL 94		HB
Viscosity	-		+
Non toxic	EEC 90/128 FDA		-
Coefficient of friction	DIN 53375		0.5
Anti-ultraviolet	-		-

Remarks:

- 1.“+”: positive “-”: negative “0”: depends.
2. All the parameters above are based on raw material but not finished products.