

ENZINRON (ESD Bakelite)

	METHOD	UNIT	VALUE
Mechanical Properties			
Specific gravity	JB/T 8149.1-2000	g/cm ³	1.3~1.5
Vertical layer bending strength	JB/T 8149.1-2000	Mpa	120
Vertical compressive strength	JB/T 8149.1-2000	%	250
Tensile strength	JB/T 8149.1-2000	Mpa	100
Electrical Properties			
Volume resistivity	JB/T 8149.1-2000	$\Omega \cdot \text{cm}$	10^{5-9}
Surface resistivity	JB/T 8149.1-2000	Ω	10^{5-9}
Others			
Adhesive Strength	JB/T 8149.1-2000		3200

Remarks:

- 1.“+”: positive “-”: negative “0”: depends.
2. All the parameters above are based on raw material but not finished products.

1/F Office Building H , Hengli Industrial Park , No.168 Xiakeng 1st Road , Longgang District , Shenzhen , China 518116 .